

REACTIVE DYES Dyeing on Cotton		"M" Dyes (Cynuric Cold Brand)	Solubility		Application Method			
			30°C G/L	(50 Oarts/1000) Common Salt	Exhaust	Batch Dyeing	Printing	
1%	4%	Product Name C.I. No.						
		RE. YELLOW M8G *Yellow 86	80	50	S	--	--	
		RE. YELLOW M4R *Orange 4	90	50	S	--	--	
		RE. YELLOW M4G *Yellow 22	50	30	S	--	--	
		RE. YELLOW M4R *Yellow 14	70	40	S	--	--	
		RE. GOLD. YELLOW MR *Yellow 44	65	40	S	--	--	
		RE. ORANGE M2R *Orange 4	100	90	S	--	--	
		RE. RED M5B *Red 2	60	45	S	--	--	
		RE. RED M8B *Red 11	70	50	S	--	--	
		RE. MAGENTA MB *Violet 13	60	40	S	--	--	
		RE. VIOLET C4R *Violet 24	60	40	S	--	--	

Substantivity	Day Light		Washing Fastness				Rubbing Fastness		Perspiration				Dischargeability	Hypochlorite Bleaching Fastness
	1/6	1/1	ISO 3		ISO 4		Dry	Wet	Alkali		Acid			
			Effect	Stain	Effect	Stain			Effect	Stain	Effect	Stain		
L	3-4	5-6	4	4	4-5	5	4	3	4-5	5	4	4-5	G	2
M	3-4	5	4-5	4	5	4-5	4	3	4	4-5	5	4-5	P	2
M	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4	4	5	G	1
M	4	5	5	4-5	5	4-5	4-5	4	4-5	5	4-5	5	P	2
H	4	5	4-5	4-5	4	4-5	4-5	3	4	4-5	4	4-5	P	2
M	3	4	4-5	4	4-5	4	4	3	4-5	4-5	4	4-5	P	2-3
H	4	4-5	4-5	4	4	4	5	4-5	5	3-4	4	4	F	1
H	4-5	4-5	4-5	4-5	4-5	4	4-5	4	5	4	4-5	4	P	4
H	3-4	3-4	4-5	4	4	4	5	4	5	4-5	4-5	5	F	3
H	3-4	3-4	4-5	4	4	4	5	4	5	4-5	4-5	5	F	3

